




TESNIT BA-C



TECHNICAL DATA SHEET

Basis

Aramide fibres, CSM

General properties and application

Gasket material for different aggressive media and with very good chemical resistance to acids and alkaline media.

Approvals

UDT

Dimensions of standard sheets

Sheet size: 1000 x 1500 mm, 1500 x 1500 mm

Thickness: 0.5 mm, 0.8 mm, 1.0 mm, 1.5 mm, 2.0 mm, 3.0 mm (other thicknesses on request)

Tolerances: Thickness: < 1 mm ± 0.1 mm, ≥ 1 mm ± 10 %, Length: ± 50 mm, Width: ± 50

Surface treatment: Treatment with graphite, PTFE and antistick coating is available on request.


Technical data

Typical values (thickness 2.0 mm)

Compressibility	ASTM F 36/J	8 %
Recovery	ASTM F 36/J	45 %
Tensile strenght	DIN 52910	10 MPa
Stress resistance	DIN 52913	
• 16h, 175°C, 50 MPa		25 MPa
Specific Leak rate	DIN 3535/6	0.06 mg/(s.m)
Thickness increase	ASTM F 146	
• HNO ₃ 40%, 18h, 23°C		10 %
• H ₂ SO ₄ 65%, 48h, 23°C		8 %
*Max. operating conditions		
Peak temperature		200°C / 392°F
Continuous temperature		150°C / 302°F
- with steam		
Pressure		60 bar / 870 psi


* Temperature and pressure represent maximum values and should not be used simultaneously. They are given only for guidance, since they depend not only on the type of gasket material but also on the assembly conditions. Very important factors are: thickness of material, nature of service medium, type of flange, surface stress. Steam application requires special consideration.

- General suitability using common installation practices under the condition of chemical compatibility.
- Max. performance is ensure through appropriate measures for joint design and gasket installation. Consultation is recommended.
- Limited application area - Technical consultation is mandatory.



This edition cancels all previous issues. Subject to change without notice.

TESNIT BA-C



The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

● Recommended	■ Recommendation depends on operating conditions	▼ Not recommended
Acetamide		
Acetic acid 10%		
Acetic acid 100%		
Acetic ester	■	
Acetone		
Acetylene		
Adipic acid		
Air		
Alum		
Aluminium acetate		
Aluminium chlorate		
Aluminium chloride		
Ammonia		
Ammonium bicarbonate		
Ammonium chloride		
Ammonium hydroxide		
Amyl acetate	■	
Aniline	▼	
Asphalt	■	
Barium chloride		
Benzene	▼	
Benzoic acid		
Boric acid		
Borax		
Butane		
Butyl alcohol	■	
Butyric acid		
Calcium chloride		
Calcium hydroxide		
Carbon disulphide	▼	
Carbon dioxide		
Chloroform	■	
Chlorine, dry		
Chlorine, wet	■	
Chromic acid	■	
Citric acid		
Copper acetate		
Creosote	▼	
Cresol	■	
Cyclohexanol		
Cyclohexanone	■	
Decaline		
Dibenzyl ether	▼	
Dimethyl formamide	▼	
Dowtherm	■	
Ethane		
Ethyl acetate	■	
Ethyl alcohol		
Ethyl chloride	▼	
Ethylene		
Ethylene glycol		
Formic acid 10%		
Formic acid 85%		
Formaldehyde		
Freon 12		
Freon 22		
Fuel oil		
Gasoline		
Glycerine		
Heptane		
Hydraulic oil (Mineral)		
Hydraulic oil (phosphate ester type)	■	
Hydraulic oil (glycol based)		
Hydrazine		
Hydrochloric acid 20%		
Hydrochloric acid 36%		
Hydrofluoric acid 10%	■	
Hydrofluoric acid 40%	▼	
Hydrogen		
Isobutane	■	
Isooctane		
Isopropyl alcohol		
Kerosene		
Lead acetate		
Lead arsenate		
Magnesium sulphate		
Malic acid		
Methane		
Methanol		
Methyl chloride	■	
Methylene dichloride	■	
Methyl ethyl ketone	■	
Milk		
Mineral oil type ASTM no. 1		
Naphtha	■	
Nitric acid 20%		
Nitric acid 40%		
Nitric acid 96%	▼	
Nitrobenzene	▼	
Nitrogen		
Octane		
Oleic acid		
Oleum		▼
Oxalic acid		
Oxygen		
Palmitic acid		
Pentane		
Perchloroethylene	■	
Phenol	■	
Phosphoric acid		
Potassium acetate		
Potassium bicarbonate		
Potassium carbonate		
Potassium chloride		
Potassium dichromate		
Potassium hydroxide		
Potassium iodide		
Potassium nitrate		
Potassium permanganate		
Propane		
Pyridine	▼	
Salicylic acid		
Silicone oil		
Soap		
Sodium aluminate		
Sodium bicarbonate		
Sodium bisulphite		
Sodium carbonate		
Sodium chloride		
Sodium cyanide		
Sodium hydroxide		
Sodium sulphate		
Sodium sulphide		
Starch		
Steam		
Stearic acid		
Sugar		
Sulphuric acid 20%		
Sulphuric acid 96%		
Tar		
Tartaric acid		
Toluene		
Transformer oil		
Trichlorethylene	■	
Water		
White Spirit		
Xylene		

MAJ:esign_english_jezik, 21.3.2003

In order to spread the most comprehensive knowledge of our products, our highly skilled group of experts organized in the technical-service department can assist you by solving practically any sealing problem. If you need our help, contact us.

DONIT TESNIT



DONIT TESNIT d.d.
Cesta komandanta Staneta 38
1215 MEDVODE, Slovenija
telefon: +386 (01) 582 32 00
fax: +386 (01) 582 32 06, 582 32 08
E-mail: info@donittesnit.si
<http://www.donittesnit.si>